

# Primer G


**Available sizes:**

10809050 Primer G 50 g

**Accessories:**

13955050 Primer Applicator,

## Suitable for different rubber materials

2-K Primer is especially suitable for the pre-treatment of various rubber materials and metal surfaces prior to the application of WEICON Urethanes.

## Technical Data

Base	Urethane
Colour	yellowish, transparent
Mixing ratio by weight resin/hardener	32:1
Solvent content	40 - 60 %
Density of the mixture	0,95 g/cm <sup>3</sup>
Viscosity at +20°C (+68°F) according to Brookfield	40 mPa·s
Pot life at +20°C (+68°F)	15 min.
Overcoating with polyurethane	after 30 to 60 min.

## Processing

Primer G is a 2C-system, which needs to be mixed prior to the application. To do so, fill the entire content of the syringe into the bottle, then close it and shake well for approx. two minutes. Apply Primer G to the clean and dry surface and spread it evenly using a paint brush. After approx. 30 - 60 minutes, the primer has reached handling strength and can be coated with Urethane 85. During the application, we recommend an ambient temperature of 20°C at a relative air humidity below 85%.

## Storage

When unopened and stored in a normal climate (+23°C and 50 % rel. humidity), WEICON Primer G has a shelf life of 9 months.

## Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG  
(Headquarters)  
Germany  
phone +49 (0) 251 9322 0  
info@weicon.de  
www.weicon.de

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae  
www.weicon.ae

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca  
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Turkey  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr  
www.weicon.com.tr

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com  
www.weicon.com.ro

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za  
www.weicon.co.za

WEICON South East Asia Pte Ltd  
Singapore  
phone (+65) 6710 7671  
info@weicon.com.sg  
www.weicon.com.sg

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz  
www.weicon.cz

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es  
www.weicon.es

WEICON Italia S.r.l.  
Italy  
phone (+39) 0102924871  
info@weicon.it  
www.weicon.it