

Plast-o-Seal®



**permanently plastic universal sealant
solvent free with no unpleasant odour enables immediate
assembly**

For sealing the smooth treated flanges of machine, gearbox and motor casing flanges. To improve the performance of both old and new gaskets made from paper, cork, felt etc. Solvent free, free of silicon, odourless, remains permanently plastic, both before and after assembly, easy joint dismantling, non corrosive, No dripping, very good resistance to most fuels, mineral oils, water, air, coolant mixtures based on methanol and glycol, antifreezes, kerosene, fluorocarbon refrigerants etc.

Technical Data

Base	Polyester resin
Colour	Blue (fluorescent)
Specific weight at +20°C (+68°F)	1,15 g/cm ³
Max. Gap Bridging	0,10 mm
Viscosity at 25°C (+77°F) according to Brookfield	950.000 - 1.650.000 mPa·s
Processing temperature	+5 to +35 °C
Storage stability	24 months
Temperature resistance	-50 to +200 briefly to +250 °C
ISSA-Code	75.628.41/42/43
IMPA-Code	815231/32/33

Surface pre-treatment

Best results will be achieved on cleaned, degreased parts (use WEICON Surface Cleaner).

Processing

Plast-o-Seal on one surface. No ventilating necessary enables immediate assembly, immediate sealing effect. At low temperatures, carry to +20°C before application.

Storage

Shelf life: min. 24 months at room temperature (+20°C).

Safety and health

<p>When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.</p>

Available sizes:

30000090	Plast-o-Seal® 90 g
30000120	Plast-o-Seal® 120 g
30000300	Plast-o-Seal® 300 g
30000230	Plast-o-Seal® 230 g

Accessories:

13250001	Cartridge Gun,
13250002	Cartridge Gun Special,
13250009	Compressed Air Cartridge Gun,
13955072	Press Pack Dosing Tip,

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG
(Headquarters)
Germany
phone +49 (0) 251 9322 0
info@weicon.de
www.weicon.de

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae
www.weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com
www.weicon.com.ro

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za
www.weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
phone (+65) 6710 7671
info@weicon.com.sg
www.weicon.com.sg

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz
www.weicon.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es
www.weicon.es

WEICON Italia S.r.l.
Italy
phone (+39) 0102924871
info@weicon.it
www.weicon.it