

WEICON Pipe Repair Kit



The set is designed for the emergency repair of defective and damaged pipes and pipelines.

It comprises one WEICON Repair Stick Steel, a special repair tape made of fibreglass-reinforced plastic, assembly instructions and a pair of protective gloves.

The repair tape is impregnated with a special resin and activated by contact with water.

The Pipe Repair Kit can be processed without any additional tools and is used for the reliable and permanent sealing of cracks and leaks. It is very easy and quick to use and shows excellent adhesive properties, high pressure and chemical resistance as well as temperature resistance up to 150°C. Within 30 minutes, the tape is fully cured and hard-wearing.

Due to the fabric properties of the tape, the resulting high flexibility and the simple processing, the repair kit is particularly suitable for sealing leaks in bends, T-pieces or in spaces difficult to access.

It can be used on many different surfaces such as stainless steel, aluminium, copper, PVC, many plastics, fibreglass, concrete, ceramics and rubber.



Technical Data

Technical Data Repair Stick Steel

| | |
|---------------------------------------|--------------------------|
| Composition | Epoxy resin steel-filled |
| Composition | pasty |
| Colour after curing | dark-grey |
| Mixing ratio by volume resin/hardener | 1:1 |
| Density of the mixture | 2,0 g/cm ³ |
| Gap bridging max. | 15 mm |
| Processing temperature | +10 to +35 °C |

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

| | |
|--|--|
| Curing temperature | +6 to +40 °C |
| Polt life for 25gr preparation and +20°C (+68°F) | 4 min. |
| Handling strength (35% strength) after | 10 min. |
| Capable of bearing mechanical loads (50% strength) after | 60 min. |
| Final strength (100%) after | 24 h |
| Pressure (DIN 53281-83) | 80 N/mm ² |
| Medium shear strength after 7 days at +20°C (+65°F) DIN EN 1465 at | Steel sandblasted: 4,1 N/mm ² |
| Shore hardness D | 75 |
| Thermal conductivity (ASTM D 257) | 0,6 W/m·K |
| Linear shrinkage | < 1 % |
| Electrical resistance (ASTM D 149) | 5•10 ¹¹ Ohm/cm |
| Dielectric strength (ASTM D 149) | 3,0 kV/mm |
| Thermal expansion coefficient (ISO 11359) | 30-40 x 10 ⁻⁶ K ⁻¹ |
| Temperature resistance | -50 to +120 briefly +150 °C |

Technical Data Repair Tape

| | |
|--|----------------------|
| Pot-life at +20°C (+68°F) | 3 - 5 min. |
| Handling strength (35% strength) after | 7 - 10 min. |
| Final hardness after | 30 min. |
| Tensile strength | 35 N/mm ² |
| Compressive strength | 150 bar |
| Shore D (ATSM D 1706) | 70 |
| Temperature resistance | to +150 °C |

Information about surface pre-treatment and processing can be found in the manual.

Storage

Store WEICON Pipe Repair Kit at room temperature (but up to max. +25°C) in a dry place. Unopened containers can be stored for 24 months at temperatures from +18 to +25°C.

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

| | |
|----------|--------------------------------------|
| 10710001 | WEICON Pipe Repair Kit 5 cm x 1,5 m |
| 10710002 | WEICON Pipe Repair Kit 5 cm x 3,6 m |
| 10710003 | WEICON Pipe Repair Kit 10 cm x 3,6 m |

WEICON GmbH & Co. KG
(Headquarters)
Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com
www.weicon.com.ro

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
phone (+65) 6710 7671
info@weicon.com.sg

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz
www.weicon.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es
www.weicon.es

WEICON Italia S.r.l.
Italy
phone (+39) 0102924871
info@weicon.it
www.weicon.it